







			CREATION 55 CLIC SYSTEM ACOUSTIC		
DESCRIPTION		CREATION 55 CLIC SYSTEM		GERFLOR ACOUSTIC 15dB	CREATION 55 CLIC SYSTEM + GERFLOR ACOUSTIC 15dB
Total Thickness	EN ISO 24346 (EN 428)	mm	5.00	0.93	5.93
	ASTM F386	inch	0.2	0.04	0.23
Thickness of the wearlayer	EN ISO 24340 (EN 429)	mm	0.55	-	0.55
	ASTM F410	inch	0.02	-	0.02
Weight	EN ISO 23997 (EN 430)	g/m <sup>2</sup>	8260	200	8460
Size	EN ISO 24342 (EN 427)	mm	176x1000 / 360x696 / 204x1239	-	176x1000 / 360x696 / 204x1239
	ASTM F 536	inch	6.9"x39.4" / 14.2"x27.4" / 8"x48.8"	-	6.9"x39.4" / 14.2"x27.4" / 8"x48.8"
Length of sheet	EN ISO 24341 (EN 426)	m	-	15	-
Width of sheet	EN ISO 24341 (EN 426)	cm	-	100	-
<b>CLASSIFICATION</b>					
Norm/Product Specification	-	-	EN ISO 10582 (EN 649)	-	-
	ASTM F 1700	-	Class III Type B	-	-
European Classification	EN ISO 10874 (EN 685)	class	33 - 42	-	33-42
Fire Rating	EN 13 501-1	class	Bfl-s1	Efl	Bfl-s1
Static Electrical Propensity	EN 1815	kV	< 2	-	-
Slip Resistance Wet	DIN 51130	class	R9/R10/R11*	-	R9-R10*
<b>PERFORMANCES</b>					
Wear Resistance	EN 660.2	mm <sup>3</sup>	< 2.0	-	≤ 2.0
Wear Group	(EN 649)	group	T	-	T
Type Binder content	EN ISO 10582	type	I	-	I
Room Impact	NF S 31074	dB	77	-	70
Impact sound insulation	EN ISO 717-2	dB	5	-	15
Dimensional Stability	EN ISO 23999 (EN 434)	%	≤ 0.15	-	≤ 0.15
Residual Indentation	EN ISO 24343-1 (EN 433)	mm	≤ 0.10	0.16	0.13
Castor chair test	ISO 4918 (EN 425)	-	OK	-	OK
Thermal Conductivity	EN ISO 10456 (EN 12 524)	W/(m.K)	0.25	-	-
Colour Fastness	EN 20 105 - B02	degree	≥ 6	-	≥ 6
Surface Treatment	-	-	PUR+	-	PUR+
Chemical Products Resistance	EN ISO 26987 (EN 423)	-	OK	-	OK
<b>ENVIRONMENT / INDOOR AIR QUALITY</b>					
TVOC after 28 days	ISO 16000-6	µg/ m3	< 100	-	< 100
Certification	-	-	Floorscore®	-	-
<b>CE MARKING</b>					
	EN 14041			-	
					

\* / Slip Resistance Wet : details on web site gerflor.